

## Processing advice

**Product name:** Bio-Flex® FX 1120 (previously V 141105)  
**Date of issue:** 22 February 2016

Version: 1.0

### Designation of product, preparation and manufacturer

**Trade name:** Bio-Flex® FX 1120 (previously V 141105)  
**Use of product:** Biodegradable and compostable compound for blown film extrusion. Certified (according to EN 13432) with a maximum thickness of 112 µm. The biobased carbon content (BCC) is 50 % (determined according to ASTM D6866). Used in applications such as wate bags or T-Shirt bags.  
**Manufacturer:** FKUR Kunststoff GmbH  
 Siemensring 79  
 47 877 Willich  
 Germany  
 Phone.: + 49 (0) 2154 / 92 51-0  
 Fax: + 49 (0) 2154 / 92 51-51  
 Mail: info@fkur.com  
 Web: www.fkur.com

### Processing conditions for blown film extrusion

**Machine equipment:** Standard low-density polyethylene screw.  
**Machine settings:**

Feeding Zone	60	[°C]
Zone 1	160	[°C]
Zone 2	160	[°C]
Zone 3	165	[°C]
Zone 4	170	[°C]
Adapter	170	[°C]
Die	175	[°C]
Mass temperature	max. 190	[°C]
Die gap	0.8 - 1.4	[mm]
Die diameter	up to 400 mm	[mm]
Blow up ratio	2.5 - 4	[-]

**General advice:** Start at temperatures given above. If gel particles or die lines appear, increase temperature stepwise by 5°C up to a maximum of 190°C melt temperature.

### Purging advice: blown film extrusion

**Before production:** Ensure that all temperature zones work correctly. Purge the extruder with low melting LDPE, MFR approx. 4 - 6 g/10 min using the above temperature settings. Purging time: approximately 10 - 20 minutes. We recommend to change the screen before production.  
**During production:** Use sufficient cooling for extruder and bubble, a dual lip air ring and/or inner bubble cooling system is preferred with chilled air, as the bubble stability is low when emerging from the die.  
**After production:** Purge the extruder with an LDPE (MFR 0.4 - 2.0 g/10min). Do not allow material to remain hot inside the machine for extended periods as the material will degrade.

### Drying conditions and storage

**General:** Bio-Flex® is a biodegradable plastic based on PLA and other biopolymers. Moisture content can lead to hydrolysis. Residual moisture content of more than 0.2 % can result in fish eyes and/or pin holes during processing.  
**Drying:** We recommend drying Bio-Flex® at 60°C for a period of 2 - 4 hours.  
**Storage conditions:** If not specified otherwise product life is 6 month after shipment from Sellers warehouse if product is in its original packaging, stored under dry (max. 70% relative humidity) and dark conditions (not exposed to sunlight at a temperature of 5 °C to max. 30°C (ambient temperature)). It is important to observe that a major drop in external air temperature (e.g. during transportation) can result in a development of water condensate. Prior to the processing of the material, it should be ensured that there is no condensate on the packaged product.  
**Storage conditions for finished products:** Finished products made from Bio-Flex® must be stored dry and cold. It is recommended to wrap goods in black PE liners to protect them against moisture and UV radiation. Storage time depends on processing parameters and of climate conditions in the respective area. Because of these essential and complex interacting parameters, FKUR Kunststoff GmbH cannot give any shelf life guarantees for finished products. Please notice that the conditions mentioned above depend on experience of our customers. Each customer should execute individual storage tests according to product specifications and storage requirements.

## Processing advice

**Product name:** **Bio-Flex<sup>®</sup> FX 1120 (previously V 141105)**  
**Date of issue:** 22 February 2016

Version: 1.0

### Legal notice

General:

Neither FKUR Kunststoff GmbH nor its marketing affiliates shall be responsible for the use of this information or of any product, method or equipment mentioned. Customers must undertake their own determination of this product's suitability and completeness for their own use, for the protection of the environment, for the health and safety of their employees and purchasers of their products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the seller's conditions of sale.

Brand names:

The brands "FKuR - Plastics made by nature" and "Bio-Flex" are registered trademarks of FKUR Kunststoff GmbH, according to the international 'Nice-Classifications' (NCL9), no. 01, 02 and 17.