

High Density Polyethylene SGE7252

Description:

SGE7252 is a bimodal High Density Polyethylene specially developed for the manufacturing of caps and closures that require high stress cracking resistance. The minimum biobased content of this grade is 96%, determined according to ASTM D6866.

Applications:

Caps for non-carbonated or low carbonated soft drinks, Sealants

Control Properties:

Feature	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	2.0
Density	D 792	g/cm ³	0.952

Typical Properties - Plaque¹:

Plaque Properties

Feature	Method	Units	Values
Tensile Strength at Yield (a)	D 638	MPa	26
Elongation at Yield (a)	D 638	%	9
Tensile Strength at Break (a)	D 638	MPa	32
Elongation at Break (a)	D 638	%	400
Flexural Modulus - 1% Secant (b)	D 790	MPa	1100
Environmental Stress Cracking Resistance - notch 0,3 mm; 50°C; 10% Igepal CO630 (a)	D 1693	h/F50	15

¹ Test specimens from compression molded plaque according to ASTM D4703. Plaque Thickness: a) 2mm. b) 3mm c) 6mm

* NB = No break

Final Remarks¹:

- This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA - Food and Drug Administration in force on the date of publication of this specification. The additives present are covered in appropriate regulation by FDA
- The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
- In some applications, Braskem has developed tailor-made resins to reach specific requirements.
- In case of doubt regarding utilization, or for other applications, please contact our Technical Assistance.
- For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 25087-34-7.
- The mentioned values in this report can be changed at any moment without Braskem previous communication.
- Unless specified, Braskem does not recommend the use of this grade for the fabrication of packages, parts or any other type of product designed to medical and/or pharmaceutical applications.
- The content of this Data Sheet replaces previous revisions published for this product.