

## Low Density Polyethylene SBC818

### Description:

SBC818 is a low density polyethylene developed for coating process, it presents very good optical properties, low neck-in, good film stability, and good adhesion on porous substrate. Additives free.

The minimum biobased content of this grade is 95%, determined according to ASTM D6866.

### Applications:

General use articles, Masterbatches, Specialty Film - Extrusion Coating

### Processes:

Extrusion Coating

### Control Properties:

Feature	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	8.3
Density	D 1505	g/cm <sup>3</sup>	0.918

### Typical Properties - Films:

Blow film Properties (a)

Feature	Method	Units	Values
Tensile Strength at Break (MD/TD)	D 882	MPa	25/20
Elongation at Break (MD/TD)	D 882	%	380/870
Dart Drop Impact	D 1709	g/F50	70
Elmendorf Tear Strength (MD/TD)	D 1922	gF	ND(b)/56
Haze	D 1003	%	8
Gloss - Angle 60°	D 2457	%	76

(a) LDPE: 25 µm thick film, obtained from a 75 mm extruder, with blow up ratio of 2:1, die gap 1 mm and Die rate 1,75 kg/h.cm (MD = Machine Direction and TD = Transversal Direction). (b) ND: Not Determined

### Final Remarks:

- This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA - Food and Drug Administration in force on the date of publication of this specification. The additives present are covered in appropriate regulation by FDA.
- The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
- In some applications, Braskem has developed tailor-made resins to reach specific requirements.
- In case of doubt regarding utilization, or for other applications, please contact our Technical Assurances Area.
- For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 9002-88-4
- The mentioned values in this report can be changed at any moment without Braskem previous communication.
- Braskem does not recommend this grade for packages, parts or any kind of product manufacture that will be used for storage or contact with solution that will have internal contact with human body.
- This resin does not contain the substance Bisphenol A (BPA, CAS #80-05-7) in its composition.