

Ethylene-Vinyl Acetate Copolymer SVT2180**Description:**

SVT2180 is a copolymer of renewable ethylene with Vinyl Acetate (EVA) mainly used for the production of crosslinked foam sheets and other parts. It is a product with easy processability and high compatibility with mineral fillers, and thermoplastic and elastomeric resins. Other important characteristics are elasticity, flexibility, excellent stress cracking resistance (ESCR), chemical resistance, and low temperature strength. The exclusive morphologic characteristics give an outstanding crosslinkability. The components produced with SVT2180 have the following properties: low weight, resistance to deformation, low shrink, high capacity of sticking and color retention.

The minimum biobased carbon content of this grade is 80%, determined according to ASTM D6866.

Additives:

Antioxidant

Control Properties:

Característica	Método	Unidades	Valores
Melt Flow Rate (190°C/2.16kg)	ASTM D 1238	g/10 min	2.1
Vinyl-Acetate Content	ASTM-D-5594-98	%	19

Typical Properties - EVA:

Plaque Properties (a)

Característica	Método	Unidades	Valores
Density	D 1505 / D 792	g/cm ³	0.940
Tensile Strength at Break	D 638	MPa	19
Elongation at Break	D 638	%	750
5% Secant Modulus	D 638	MPa	33
Hardness	D 2240	Shore A / D	89/38
Melting Point	D 3418	°C	86
Vicat Softening Temperature at 10 N	D 1525	°C	61

(1) Braskem test method available for customers. (a) Test specimens prepared from compression molded plate according to ASTM D 4703. (b) Compression molded 2 mm thickness, 0.3 mm notched-plaques; 100% Igepal; 50°C.

Final Remarks

1. It is the sole responsibility of the Client/Purchaser of this Product to verify the suitability of this Product and its use for the intended use and to ensure compliance with legal and regulatory requirements applicable to the final product.
2. The technical guidance eventually rendered to the Client/Purchaser of the Product by Braskem about the Product does not characterize a performance guarantee for the intended application, nor does it exempt the Client/Purchaser from the responsibilities described in item 1 above.
3. Any application information about the Product does not mean that Braskem knows or has validated the productive process of the Client/Purchaser or the adequacy of the Product for the intended application. All warranties of merchantability or fitness for a particular purpose, express or implied, are expressly excluded.
4. The information provided herein is of the date hereof and Braskem may update, revise or amend the information contained herein at any time and without previous notice. The Client/Purchaser shall consult www.braskem.com to verify any updates to this information.
5. For regulatory information associated with the Product and its source, please consult the Regulatory Information Sheet (RIS). For other requests, please contact Braskem's Technical Services area.
6. The information contained herein is provided based on the best of Braskem's knowledge, indicating typical values of the properties of the Product, and such values shall not be considered absolute or as a guarantee.