

Technical data sheet

Product name: HDPE Blow Red
Date of issue: 18 April 2023

Version: 1.1

Designation of product, preparation and manufacturer

Trade name: HDPE Blow Red
Use of product: Post industrial recycled high density polyethylene suitable for blow moulding applications in various colours.

Distributor: FKUR Kunststoff GmbH
Siemensring 79
D - 47 877 Willich
Phone: + 49 (0) 2154 / 92 51-0
Fax: + 49 (0) 2154 / 92 51-51
Mail: info@fkur.com
Web: www.fkur.com

Mechanical properties

Modulus of elasticity	670	[MPa]	ISO 527
Tensile strength	20	[MPa]	ISO 527
Tensile strain at tensile strength	15	[%]	ISO 527
Tensile stress at break	11	[MPa]	ISO 527
Tensile strain at break	450	[%]	ISO 527
Notched impact strength (Charpy), RT	24	[kJ/m ²]	ISO 179-1/1 eA
Impact Strength (Charpy), RT	125	[kJ/m ²]	ISO 179-1/1 eU

The values listed have been established on standardized test specimens (DIN EN ISO 3167, type A) at standard temperature and humidity conditions.

Physical properties

Melt flow rate (190 °C/21.6 kg)	19	[g/10 min]	ISO 1133
Melting temperature	130 - 145	[°C]	
Density	0.95	[g/cm ³]	ISO 1183

The figures should be regarded as guide values only. Under certain conditions the properties can be influenced to a significant extent by the processing conditions.

Technical data sheet

Product name: HDPE Blow Red
Date of issue: 18 April 2023

Version: 1.1

Processing and Handling Information

General

This material is a post industrial recycled polyolefin. Due to its chemical structure, it should be handled and processed like standard polyolefins.

Drying

If packed in its original packaging and stored in good conditions drying is not necessary.
If moisture uptake is too high the material can be dried at 60 °C for a period of 2 - 4 hours.

Storage

If not specified otherwise product life is 6 month after shipment from Sellers warehouse if product is in its original packaging, stored under dry (max. 70% relative humidity) and dark conditions (not exposed to sunlight at a temperature of 5 °C to max. 30°C (ambient temperature). It is important to observe that a major drop in external air temperature (e.g. during transportation) can result in a development of water condensate. Prior to the processing of the material, it should be ensured that there is no condensate on the packaged product.
Finished products shall be stored dry and cold. It is recommended to wrap goods in black PE liners to protect them against moisture and UV radiation. Storage time depends on processing parameters and of climate conditions in the respective area. Because of these essential and complex interacting parameters a shelf life guarantees for finished products cannot be given. Each customer should execute individual storage tests according to product specifications and storage requirements.

Legal notice

Neither KASKADA LTD nor its marketing affiliates shall be responsible for the use of this information or of any product, method or equipment mentioned. Customers must undertake their own determination of this product's suitability and completeness for their own use, for the protection of the environment, for the health and safety of their employees and purchasers of their products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the seller's conditions of sale.